



Specifications for applying
SportMaster Pro Cushion System
over asphalt tennis court surfaces

CMT - 26

Revised: 7/04

PRODUCT NAME:

SportMaster Pro Cushion System over asphalt tennis court surfaces

MANUFACTURER:

ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-326-1994
Fax: 419-626-5477
www.thorworks.com

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit
www.sealmaster.net to find the location near you.

1. SCOPE:

1.1
The following specifications pertain to the application of the SportMaster Pro Cushion System over asphalt tennis court surfaces.

2. SURFACE PREPARATION:

2.1
New asphalt surfaces must cure 30 days prior to application. The surface must be cleaned entirely of dust, dirt, debris, and all loose materials.

2.2
Fill all cracks with SportMaster Acrylic Crack Patch or suitable crack filler.

2.3
Level depressions or "bird baths" (1/8 inch or deeper) with SportMaster Acrylic Patch Binder or Acrylic Resurfacer patching mix.

2.4
Apply one or two coats of SportMaster Acrylic Resurfacer as required by surface roughness and porosity to provide a smooth underlayment for application of the SportMaster Color System.

3. APPLICATION OF SPORTMASTER PRO CUSHION SYSTEM:

3.1
To properly prepared surface, apply three (3) coats of CushionMaster II followed by two (2) coats of CushionMaster I in accordance with SportMaster mixing and application instructions.

3.2
Apply three (3) coats of CushionMaster Color Concentrate in accordance with manufacturer's mixing and application instructions.

4. LINE MARKINGS:

4.1
Line markings shall be laid out according to United States Tennis Association specifications.

4.2
After masking tape has been laid apply SportMaster Stripe Rite line primer to seal voids between masking tape and court surface to prevent "bleed under" when SportMaster Line Paint is applied.

4.3
Apply a minimum of one coat of SportMaster Line Paint.

5. GENERAL:

5.1
All work shall be performed in a workmanlike manner. All containers and debris shall be removed from job when completed.